



COMMERCIAL - TECHNICAL DATA / Tecnologia

FABRIC NAME

HALF PANAMA

YARN/CONSTRUCTION:	16S+16S*12S+12S/112*52	COMP:	100%COTTON
		H.S CODE	52092100
Test Method for Woven Fabrics			STANDARD (PFD/PFDPP)
Width / Ancho NTC 228-2011		In	Cms
	Phisic / Fisico	59	150
	Useful / Util	57	145
Weight /Peso ASTM D 3776-2009		Oz/syd	Gsm
		7.5	255
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	4%	
	Trans / Transversal	4%	
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	2%	
	Trans / Transversal	2%	
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4	
	Stain / Transf	4	
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4	
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	3	
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4	
	Wet / Húmedo	3	
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4	
	Stain / Transf	4	
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3	
Type of fabric / Tipo de tejido		Woven	

Recommendations:

