



COMMERCIAL - TECHNICAL DATA / Tecnologia



BASIC ECO

48% RECYCLED POLY 48% POLY 4% ELASTANE

| Test Method for Knit Fabrics | | STANDAR (estandar) | DIGITAL PRINT |
|---|---------------------|--------------------|---------------|
| Width / Ancho (In) NTC 228-2011 | Phisic / Físico | 63 | 63 |
| | Useful / Util | 62 | 61 |
| Weight / Peso (Oz/syd) ASTM D 3776-2009 | | 7.6 | 7.7 |
| Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15 | Lenght / Longitud | 5% | 5% |
| | Trans / Transversal | 4% | 4% |
| Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005 | Lenght / Longitud | 3% | 3% |
| | Trans / Transversal | | |
| Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007 | Change / Cambio | 4 | 4 |
| | Stain / Transf | 3 | 3 |
| Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007 | Stain / Transf | 4 | 4 |
| Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990 | Change / Cambio | 4 | 4 |
| Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007 | Dry / Seco | 4 | 4 |
| | Wet / Húmedo | 3 | 3 |
| Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007 | Change / Cambio | 4 | 4 |
| | Stain / Transf | 3 | 3 |
| Pilling / Pilling (Photographic) NTC 2051-2 / 2003 | | 3 | 3 |
| Type of fabric / Tipo de tejido | | | Knit |

Recommendations:

Rest for 20 to 24 hours before cutting.
Use suitable thread for light fabrics and a ball point needle.
Wash with clothes of the same color.



Reviewed by

[Signature]
ANDRES LOPEZ