



**COMMERCIAL - TECHNICAL DATA / Tecnologia**



**CANOA ECO LIGHT**  
86% MICROFIBER RECYCLED POLY  
14% LYCRA

Test Method for Knit Fabrics		STANDAR (estandar)	DIGITAL PRINT
Width / Ancho (In) NTC 228-2011	Phisic / Físico	61	61
	Useful / Util	60	59
Weight / Peso (Oz/syd) ASTM D 3776-2009		4.6	4.7
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	5%	5%
	Trans / Transversal	4%	4%
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	3%	3%
	Trans / Transversal		
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4	4
	Stain / Transf	3	3
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4	4
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	4	4
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4	4
	Wet / Húmedo	3	3
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4	4
	Stain / Transf	3	3
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3	3
Type of fabric / Tipo de tejido			Knit

Tariff code white: 6004100000

**Recommendations:**  
Rest for 20 to 24 hours before cutting.  
Recommend testing before any treatment or application other than cutting and sewing.

**Reviewed by**  
  
**ANDRES LOPEZ**