




COMMERCIAL - TECHNICAL DATA / Tecnologia

ARENA LT

100% POLYESTER

Test Method for Woven Fabrics		STANDAR (estandar)	DIGITAL PRINT
Width / Ancho (In) NTC 228-2011	Phisic / Físico	57	57
	Useful / Util	56	55
Weight / Peso (Oz/syd) ASTM D 3776-2009		5.9	6
Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15	Lenght / Longitud	4%	4%
	Trans / Transversal	3%	3%
Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005	Lenght / Longitud	3%	3%
	Trans / Transversal		
Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007	Change / Cambio	4	4
	Stain / Transf	3	3
Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007	Stain / Transf	4	4
Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990	Change / Cambio	4	4
Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007	Dry / Seco	4	4
	Wet / Humedo	3	3
Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007	Change / Cambio	4	4
	Stain / Transf	3	3
Pilling / Pilling (Photographic) NTC 2051-2 / 2003		3	3
Type of fabric / Tipo de tejido			Woven
			Reviewed by
Recommendations: Vacuum periodically. Sew with a round point needle and polyester thread for greater resistance. Graduate the length of the seam between 5 and 7 stitches per inch.			 ANDRES LOPEZ
